

# Noelson Chemicals

www.noelson.com

## Formulation Guideline Anti-Static Coating for Terrace

### Guideline:

#### Part A

Product Name	Suggested Amount %
Epoxy resin	33.0
Xylene	16.5
Butyl alcohol	7.0
Reactive diluent	5.0
TiO <sub>2</sub>	5.0
Noelson™ leveling agent	0.3
Degassing agent	0.2
Fumed silica	0.5
Noelson™ Conductive Mica Powder EC-300	23.0
Heavy calcium carbonate	9.5

#### Part B

Product Name	Suggested Amount %
Epoxy resin hardener	100.0

A/B = 4:1 (by weight)

### Disclaimer:

The guideline is provided for informational purposes only.